

EKOKAT REPAIR TCK

Repair Mortar - Thick



DESCRIPTION

The product is a cement-based, micro fiber-reinforced, high-strength, thick repair mortar containing mineral aggregates of a special particle size and chemical additives enhancing product performance.

TECHNICAL SPECIFICATIONS

Appearance	Grey
Particle Size	<1.5 mm
Mixing Ratio	6-6.5 liters of water /25 kg
Amount of Consumption	1.3 kg/m ² for a thickness of 1 mm
Application Temperature	+5 °C to +35 °C
Time for Use	40-60 minutes
Crustation Time	30 minutes
Time Until Complete Freezing	21 days
Toxicity	Non-toxic
Splice Strength	>1.0 N/mm ²
Slippage	> 0.5 mm

* The above values are valid for + 23°C and 50% relative humidity. The time is shortened at high temperatures and extended at low temperatures.

AREAS OF USE

It is used at reinforced concrete buildings, gross concrete, prefabricated concrete, and gas concrete applications, for repair and plastering of surfaces, for repair of damaged surfaces before application of coats such as ceramic and tiles, and for plastering and repair of walls, edges, corners, and ceilings.

Date: 02.03.2017 Revision: 00

ÇULLAS YAPI MALZEMELERİ SANAYİ ve DİŞ TİCARET A.Ş.
Çoraklar Mahallesi 5024 Sokak No:10 Aliğa Organize Sanayi Bölgesi - Aliğa / İzmir
TURKEY
T. +90 216 457 80 10 F. +90 216 457 82 60
info@ekokat.com www.ekokat.com



EKOKAT REPAIR TCK

Repair Mortar - Thick

BENEFITS

It is easy to prepare and apply. It provides high adherence on concrete and plaster-applied surfaces. It gives proper working time. It does not lead to drift at vertical applications. It has high adhesion properties. It is resistant to water and frost. It is not impacted from thermal differences.

INSTRUCTIONS FOR USE

The surface should be clean, and all the residues (e.g. grease, dirt, corrosion) that will prevent adhesion on the surface should be cleaned. The surface to be repaired should be saturated with water several hours in advance. No free water should remain on the surface during application. 25 kg of EKOKAT REPAIR - TCK mortar is slowly poured into 5-6 liters of clean water and is then mixed with a low speed (400-600 rpm) mixer or a trowel until a homogenous mixture is obtained. The mortar is allowed to rest for 5 minutes and mixed again for 1 to 2 minutes once before application. The mortar should be used in thirty minutes. The mortar should not be used if its usage time has expired and it has been scabbed. The mortar should be applied at the specified application temperature, and protected from direct sun, wind and frost. The mortar is applied with a trowel with a thickness of 1-5 mm. After the mortar loses its water content, water is sprinkled on it and the desired surface is obtained with a steel and wooden trowel. It must be protected from evaporation with special curing materials or wet sacks for 24 to 48 hours after application.

PACKAGING

25 kg PE reinforced craft bags.

64 shrink bags on one palette (110x110 cm).

STORAGE CONDITIONS AND SHELF LIFE



No more than two palettes should be placed on top of each other in their unopened original packaging, in a cool and dry environment. Shelf life is 12 months from date of production under suitable storage conditions.

SAFETY MEASURES

Work clothes, protective gloves, goggles, and masks suitable for workers health and safety should be used during the application. Due to irritant effects of uncured material, it should be washed with plenty of water and soap immediately in case of contact with skin and eyes. If swallowed, seek medical advice immediately. No food and drink should be brought into application areas. Store it out of reach of children. Please refer to the safety data sheet for further information.

RESPONSIBILITY

Our Company may not be held liable for any application errors that might be suffered if the product is not used for its intended purposes, or if it is failed to conform to the conditions and proposals specified above regarding technical application. This technical data sheet contains information that is current as of the date of issuance hereof. The manufacturer hereby reserves its right to change this data sheet at any time.

■ ■ ■ ■ EK 4002.010.25	 Grey
■ ■ ■ ■ EK 4003.010.25	 White

Date: 02.03.2017 Revision: 00

ÇULLAS YAPI MALZEMELERİ SANAYİ ve DİŞ TİCARET A.Ş.
Çoraklar Mahallesi 5024 Sokak No:10 Aliğa Organize Sanayi Bölgesi - Aliğa / İzmir
TURKEY
T. +90 216 457 80 10 F. +90 216 457 82 60
info@ekokat.com www.ekokat.com

